



## [ WME502, WE502 S4, WE502 S3, WE502 series ]

피삭재	합금강, 탄소강		프리하든강		스테인리스강		고경도강	
	Alloy Steels Carbon Steels (SCM, SNCM, S45C)		Prehardened Steels (NAK, CENA, KP4)		Stainless Steels (SUS)		Hardened Steels (SKD, SKT, STAVAX)	
경도	~HRc35		HRc35~HRc45				HRc45~HRc55	
강도	~1100N/mm <sup>2</sup>		1100~1500N/mm <sup>2</sup>				1500~2000N/mm <sup>2</sup>	
외경(mm)	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
2.0	11,560	190	7,560	120	6,300	90	5,040	35
3.0	8,920	210	5,560	140	4,620	120	3,360	40
4.0	7,560	300	4,620	180	3,880	150	2,940	40
5.0	6,300	320	3,780	190	3,160	160	2,320	50
6.0	5,560	350	3,360	220	2,840	180	2,000	55
8.0	4,200	380	2,520	200	2,100	180	1,680	75
10.0	3,260	330	2,000	160	1,680	160	1,360	60
12.0	2,740	280	1,680	130	1,360	130	1,160	55
16.0	2,200	220	1,360	110	1,060	110	900	40
20.0	1,680	170	1,060	80	840	80	680	30
25.0	1,360	130	840	70	680	60	540	20

RPM = rev. / min.  
FEED = mm / min.




(UP TO Ø3:0.2D)



## [ WE522 series ]

피삭재	합금강, 탄소강		프리하든강		고경도강	
	Alloy Steels Carbon Steels (SCM, SNCM, S45C)		Prehardened Steels (NAK, CENA, KP4)		Hardened Steels (SKD, SKT, STAVAX)	
경도	~HRc35		HRc35~HRc45		HRc45~HRc55	
강도	~1100N/mm <sup>2</sup>		1100~1500N/mm <sup>2</sup>		1500~2000N/mm <sup>2</sup>	
외경(mm)	RPM	FEED	RPM	FEED	RPM	FEED
2.0	6,300	60	5,040	50	3,150	25
3.0	4,410	70	3,570	60	2,200	30
4.0	3,570	85	2,840	70	1,790	35
5.0	3,050	105	2,420	85	1,580	40
6.0	2,630	125	2,100	105	1,370	50
8.0	2,000	135	1,580	105	1,050	50
10.0	1,680	135	1,370	105	840	50
12.0	1,370	105	1,160	95	700	40
16.0	1,160	95	890	75	560	35
20.0	840	70	680	50	420	25

RPM = rev. / min.  
FEED = mm / min.



(UP TO Ø3:0.4mm)

